

TECHNIWELDUSA

ATLANTA JACKSON NEWTON YOUNGSTOWN HOUSTON
P: 800-445-2152 P: 800-647-7144 P: 800-222-1113 P: 877-286-1868 P: 877-674-5586
F: 404-699-7800 F: 800-748-9973 F: 828-464-4884 F: 412-357-2181 F: 832-308-1985

TYPICAL MATERIAL TEST REPORT

ITEM CLASSIFICATION	
ALLOY	SPECIFICATION
RG45	AWS A5.2
APPLICATIONS	
Used to join wrought Iron. General purpose oxyfuel gas welding rod.	

TYPICAL CHEMICAL COMPOSITION						
ELEMENT	C	Mn	Si	S	P	
AVERAGE	0.07	0.25	0.07	0.03	0.03	